

IN THE CLAIMS

Please amend the claims as follows:

Claim 1 (Original): A method for reducing a chromium-containing material, comprising a mixing step of mixing a chromium-containing material comprising chromium oxide and iron oxide and a carbonaceous reductant to provide a mixture; and a reducing step of heating, and reducing the mixture with a rapid temperature rise by radiation heating in a moving hearth furnace to provide a reduced mixture.

Claim 2 (Original): The method for reducing a chromium-containing material according to Claim 1, wherein the average rate of raising the temperature of the mixture in the reducing step is 13.6°C/s or higher in the period from the initiation of the radiation heating of the mixture until the mixture reaches $1,114^{\circ}\text{C}$.

Claim 3 (Currently Amended): The method for reducing a chromium-containing material according to Claim 1 ~~or 2~~, wherein the reducing step is performed at $1,250^{\circ}\text{C}$ to $1,400^{\circ}\text{C}$.

Claim 4 (Currently Amended): The method for reducing a chromium-containing material according to ~~any one of Claims 1 to 3~~ Claim 1, further comprising a reducing and melting step of melting the reduced mixture provided in the reducing step by successive radiation heating to provide a reduced molten material.

Claim 5 (Original): The method for reducing a chromium-containing material according to Claim 4, further comprising a solidifying step of cooling and solidifying the reduced molten material provided in the reducing and melting step in the moving hearth

furnace to provide a reduced solid; and a separating step of separating the reduced solid into metal and slag.

Claim 6 (Currently Amended): The method for reducing a chromium-containing material according to Claim 4 ~~or 5~~, wherein the reducing step is performed at 1,250°C to 1,400°C; and the reducing and melting step is performed at a temperature higher than that in the reducing step within the range of 1,350°C to 1,700°C.

Claim 7 (Currently Amended): The method for reducing a chromium-containing material according to ~~any one of Claims 1 to 6~~ Claim 1, wherein a carbonaceous atmosphere-adjusting agent is charged together with the mixture onto the hearth of the moving hearth furnace in the reducing step.